



### Features/Applications

GREMTUBE® GMW and GMWA are medium wall, halogen free, irradiated polyolefin heat shrink tubing (GMW), with adhesive (GMWA).

GREMTUBE® GMW and GMWA offers good electrical insulation properties, high resistance to impact, abrasion and UV radiation. 3:1 shrink ratio allows it to fit over irregular shapes and large connectors.

GREMTUBE® GMW and GMWA are suitable for a variety of low voltage (up to 15kV) electrical equipment and cable connections in wet environments such as marine vessels, off-shore oil platforms, shipyard and harbor applications when zero halogen properties are required.

### Various

Standard colour: Black.

### Specifications

UV resistant.

### Dimensions



Reference GREMTUBE® GMW / GMWA	As supplied (mm)	After recovery (mm)		Standard Length (m)
	Inside Diameter Min. (D)	Inside Diameter Max. (d)	Total Wall Thickness Nom. (t)	
008,0	8,0	2,0	2,00	1,2
009,0	9,0	3,0	2,00	1,2
012,0	12,0	4,0	2,00	1,2
016,0	16,0	5,0	2,20	1,2
019,0	19,0	6,0	2,50	1,2
022,0	22,0	6,0	2,50	1,2
025,0	25,0	8,0	2,50	1,2
028,0	28,0	6,0	2,50	1,2
033,0	33,0	8,0	2,50	1,2
035,0	35,0	12,0	2,50	1,2
040,0	40,0	12,0	2,50	1,2
045,0	45,0	13,0	2,50	1,2
055,0	55,0	16,0	2,70	1,2
065,0	65,0	19,0	2,80	1,2
075,0	75,0	22,0	3,00	1,2
085,0	85,0	25,0	3,00	1,2
095,0	95,0	25,0	3,00	1,2
115,0	115,0	34,0	3,00	1,2
130,0	130,0	36,0	3,00	1,2
140,0	140,0	42,0	3,00	1,2
160,0	160,0	50,0	3,00	1,2
175,0	175,0	58,0	3,00	1,2
200,0	200,0	65,0	3,00	1,2
230,0	230,0	75,0	3,00	1,2
260,0	260,0	85,0	3,00	1,2

● Cut pieces available on request

### Property

		Values	Test Methods
Physical	Working temperature	-55°C to +105°C	-
	Longitudinal change	-10% to 0%	-
	Tensile strength	≥ 12 MPa	ASTM D 2671
	Elongation at break	≥ 400%	
	Tensile strength	≥ 12 MPa	ASTM D 2671
	Elongation at break	≥ 350%	
	Heat shock	4h @ 200°C	ASTM D 2671
Electrical	Low temperature flexibility	4h @ -55°C	ASTM D 2671
	Dielectric strength	≥ 15 kV/mm	ASTM D 2671
	Volume resistivity	≥ 10 <sup>14</sup> Ω.cm	ASTM D 2671
Adhesive	Peel strength to steel	80 N/25 mm	ASTM D 2671
	Peel strength to XLPE	110 N/25 mm	ASTM D 2671

Recommended storage conditions: Keep in cool, dry, ventilated storage (maximum temperature of 35°C) and in closed containers.



07/02/2019 Rev5

Whilst every attempt is made to provide data that is as accurate as possible the values provided should be treated as a guide only. It remains the responsibility of the user to test the product and determine suitability. GREMTEK shall not be held responsible for any loss or defect resulting from incorrect, improper or inappropriate use of this product.