

MEDIUM & HEAVY WALL TUBING GREMTUBE® GREN-F / GREA-F

Halogen free, heavy wall tubing (GREN-F), with adhesive (GREA-F)





















GREMTUBE® GREN-F and GREA-F are halogen free, heavy wall irradiated polyolefin heat shrink tubing (GREN-F), with adhesive (GREA-F).

GREMTUBE® GREN-F and GREA-F offers good electrical insulation and mechanical protection. It ensures total encapsulation and a stiff splice after shrinkage over the component. GREMTUBE® GREN-F and GREA-F are suitable for protection of low voltage (up to 1 kV) cable

connections when zero halogen properties and higher temperature are required.

Various

Standard colour: Black.

Specifications

UV resistant.





Difficultions										
	Reference	As supplied (mm)	After recovery (mm)		Standard Length					
	GREMTUBE® GREN-F / GREA-F	Inside Diameter Min. (D)	Inside Diameter Max. (d)	Total Wall Thickness Min. (t)						
	009,0	9,0	3,0	2,00	1,0	1,5				
	013,0	13,0	4,0	2,30	1,0	1,5				
	019,0	19,0	6,0	2,60	1,0	1,5				
	023,0	23,0	6,0	2,60	1,0	1,5				
	033,0	33,0	8,0	3,20	1,0	1,5				
	045,0	45,0	12,0	4,40	1,0	1,5				
	051,0	51,0	16,0	4,30	1,0	1,5				
	063,0	63,0	19,0	4,60	1,0	1,5				
	068,0	68,0	22,0	4,30	1,0	1,5				
	085,0	85,0	25,0	4,20	1,0	1,5				
	105,0	105,0	30,0	4,20	1,0	1,5				
	130,0	130,0	36,0	4,00	1,0	1,5				
	140,0	140,0	42,0	4,60	1,0	1,5				
	165,0	165,0	50,0	4,30	1,0	1,5				
	185,0	185,0	50,0	4,40	1,0	1,5				
Cut pieces available on request										

Cut pieces available on request

Proper	ty		Values		
Physical	Working temperature	,	-55°C to +125°C		
	Longitudinal change		± 10%	ASTM D 2671	
	Tensile strength	Unaged	≥ 18 MPa	ASTM D 638	
Elongation at break		Unaged	≥ 600%	ASTIVI D 030	
Electrical	Dielectric strength		≥ 25 kV/mm	IEC 243	
	Volume resistivity		≥ 10 ¹³ Ω.cm	IEC 93	
Chemical	Fluids resistance	-	Excellent	ISO 175-99	

Recommended storage conditions: Keep in cool, dry, ventilated storage (maximum temperature of 35°C) and in closed containers.

contact@gremtek.com





30/09/2015 Rev2

Whilst every attempt is made to provide data that is as accurate as possible the values provided should be treated as a guide only. It remains the responsibility of the user to test the product and determine suitability. GREMTEK shall not be held responsible for any loss or defect resulting from incorrect, improper or inappropriate use of this product. IS Sommer