





















# Features/Applications

GREMTEX® SNW-L is a flame retardant, halogen free, Polyamide, solution dyed, bulked multifilament, woven textile sleeve.

GREMTEX $^{\circ}$  SNW-L offers a continuous working temperature of -50 $^{\circ}$ C up to +125 $^{\circ}$ C and a superior resistance to abrasion and wearing.

GREMTEX® SNW-L is suitable for protection and containment of hose assemblies rope and wire harnesses. It is used extensively within the mining sector, heavy industry, construction equipment and automotive industries.



#### **Various**

Standard colour: Black.

Other sizes available on request.

## **Specifications**

ISO 6945 abrasion standards Mine Safety and Health Administration (MSHA) IC 171/1.

#### **Dimensions**

Difficusions		
Reference  GREMTEX® SNW-L	Flat width (mm)	Inside diameter (mm)
027,0	27,0	17,0
031,0	31,0	20,0
036,0	36,0	23,0
039,0	39,0	25,0
042,0	42,0	27,0
049,0	49,0	31,0
052,0	52,0	33,0
054,0	54,0	36,0
063,0	63,0	40,0
069,0	69,0	44,0
074,0	74,0	47,0
083,0	83,0	53,0
086,0	86,0	55,0
094,0	94,0	60,0
104,0	104,0	66,0
115,0	115,0	73,0
146,0	146,0	93,0
176,0	176,0	112,0

## Cutting

GREMTEX® SNW-L can be cut to length.

# **Packaging**

Available in 50 meters/spools.

Other packaging available upon request.

ty	Values	Test Methods
Working temperature	-50°C to +125°C	-
Melting point	+220°C	-
Material	Polyamide	-
Abrasion resistance	Very good	ISO 6945
Flammability	Approved	MSHA - IC 171/1 (Mining industry)
Fluid resistance	Very good	Gasoline, Oil, Mineral and vegetable oil, Alcohols, Diluted bases, Diluted acids, Benzene, Acetone, Ether, Carbon tetra- chloride, Chlorine based solvent
	Working temperature  Melting point  Material  Abrasion resistance  Flammability	Working temperature -50°C to +125°C  Melting point +220°C  Material Polyamide  Abrasion resistance Very good  Flammability Approved





16/03/2017 Rev0

Whilst every attempt is made to provide data that is as accurate as possible the values provided should be treated as a guide only. It remains the responsibility of the user to test the product and determine suitability. GREMTEK shall not be held responsible for any loss or defect resulting from incorrect, improper or inappropriate use of this product.